

ISSN 2518-1467 (Online),
ISSN 1991-3494 (Print)

ҚАЗАҚСТАН РЕСПУБЛИКАСЫ
ҰЛТТЫҚ ҒЫЛЫМ АКАДЕМИЯСЫНЫҢ

Х А Б А Р Ш Ы С Ы

ВЕСТНИК

НАЦИОНАЛЬНОЙ АКАДЕМИИ НАУК
РЕСПУБЛИКИ КАЗАХСТАН

THE BULLETIN

OF THE NATIONAL ACADEMY OF SCIENCES
OF THE REPUBLIC OF KAZAKHSTAN

1944 ЖЫЛДАН ШЫҒА БАСТАҒАН
ИЗДАЕТСЯ С 1944 ГОДА
PUBLISHED SINCE 1944

2

АЛМАТЫ
АЛМАТЫ
ALMATY

2018

MARCH
МАРТ
HAУРЫЗ

NAS RK is pleased to announce that Bulletin of NAS RK scientific journal has been accepted for indexing in the Emerging Sources Citation Index, a new edition of Web of Science. Content in this index is under consideration by Clarivate Analytics to be accepted in the Science Citation Index Expanded, the Social Sciences Citation Index, and the Arts & Humanities Citation Index. The quality and depth of content Web of Science offers to researchers, authors, publishers, and institutions sets it apart from other research databases. The inclusion of Bulletin of NAS RK in the Emerging Sources Citation Index demonstrates our dedication to providing the most relevant and influential multidiscipline content to our community.

Қазақстан Республикасы Ұлттық ғылым академиясы "ҚР ҰҒА Хабаршысы" ғылыми журналының Web of Science-тің жаңаланған нұсқасы Emerging Sources Citation Index-те индекстелуге қабылданғанын хабарлайды. Бұл индекстелу барысында Clarivate Analytics компаниясы журналды одан әрі the Science Citation Index Expanded, the Social Sciences Citation Index және the Arts & Humanities Citation Index-ке қабылдау мәселесін қарастыруда. Web of Science зерттеушілер, авторлар, баспашылар мен мекемелерге контент тереңдігі мен сапасын ұсынады. ҚР ҰҒА Хабаршысының Emerging Sources Citation Index-ке енуі біздің қоғамдастық үшін ең өзекті және беделді мультидисциплинарлы контентке адалдығымызды білдіреді.

НАН РК сообщает, что научный журнал «Вестник НАН РК» был принят для индексирования в Emerging Sources Citation Index, обновленной версии Web of Science. Содержание в этом индексировании находится в стадии рассмотрения компанией Clarivate Analytics для дальнейшего принятия журнала в the Science Citation Index Expanded, the Social Sciences Citation Index и the Arts & Humanities Citation Index. Web of Science предлагает качество и глубину контента для исследователей, авторов, издателей и учреждений. Включение Вестника НАН РК в Emerging Sources Citation Index демонстрирует нашу приверженность к наиболее актуальному и влиятельному мультидисциплинарному контенту для нашего сообщества.

Б а с р е д а к т о р ы

х. ғ. д., проф., ҚР ҰҒА академигі

М. Ж. Жұрынов

Р е д а к ц и я а л қ а с ы:

Абиев Р.Ш. проф. (Ресей)
Абишев М.Е. проф., корр.-мүшесі (Қазақстан)
Аврамов К.В. проф. (Украина)
Аппель Юрген проф. (Германия)
Баймуқанов Д.А. проф., корр.-мүшесі (Қазақстан)
Байпақов К.М. проф., академик (Қазақстан)
Байтулин И.О. проф., академик (Қазақстан)
Банас Иозеф проф. (Польша)
Берсимбаев Р.И. проф., академик (Қазақстан)
Велихов Е.П. проф., РҒА академигі (Ресей)
Гашимзаде Ф. проф., академик (Әзірбайжан)
Гончарук В.В. проф., академик (Украина)
Давлетов А.Е. проф., корр.-мүшесі (Қазақстан)
Джрбашян Р.Т. проф., академик (Армения)
Қалимолдаев М.Н. проф., академик (Қазақстан), бас ред. орынбасары
Лаверов Н.П. проф., академик РАН (Россия)
Лупашку Ф. проф., корр.-мүшесі (Молдова)
Мохд Хасан Селамат проф. (Малайзия)
Мырхалықов Ж.У. проф., академик (Қазақстан)
Новак Изабелла проф. (Польша)
Огарь Н.П. проф., корр.-мүшесі (Қазақстан)
Полещук О.Х. проф. (Ресей)
Поняев А.И. проф. (Ресей)
Сагиян А.С. проф., академик (Армения)
Сатубалдин С.С. проф., академик (Қазақстан)
Таткеева Г.Г. проф., корр.-мүшесі (Қазақстан)
Умбетаев И. проф., академик (Қазақстан)
Хрипунов Г.С. проф. (Украина)
Юлдашбаев Ю.А. проф., РҒА корр.-мүшесі (Ресей)
Якубова М.М. проф., академик (Тәжікстан)

«Қазақстан Республикасы Ұлттық ғылым академиясының Хабаршысы».

ISSN 2518-1467 (Online),

ISSN 1991-3494 (Print)

Меншіктенуші: «Қазақстан Республикасының Ұлттық ғылым академиясы»РҚБ (Алматы қ.)

Қазақстан республикасының Мәдениет пен ақпарат министрлігінің Ақпарат және мұрағат комитетінде
01.06.2006 ж. берілген №5551-Ж мерзімдік басылым тіркеуіне қойылу туралы куәлік

Мерзімділігі: жылына 6 рет.

Тиражы: 2000 дана.

Редакцияның мекенжайы: 050010, Алматы қ., Шевченко көш., 28, 219 бөл., 220, тел.: 272-13-19, 272-13-18,
www: nauka-nanrk.kz, bulletin-science.kz

© Қазақстан Республикасының Ұлттық ғылым академиясы, 2018

Типографияның мекенжайы: «Аруна» ЖК, Алматы қ., Муратбаева көш., 75.

Г л а в н ы й р е д а к т о р
д. х. н., проф. академик НАН РК
М. Ж. Журинов

Р е д а к ц и о н н а я к о л л е г и я:

Абиев Р.Ш. проф. (Россия)
Абишев М.Е. проф., член-корр. (Казахстан)
Аврамов К.В. проф. (Украина)
Апель Юрген проф. (Германия)
Баймуканов Д.А. проф., чл.-корр. (Казахстан)
Байпаков К.М. проф., академик (Казахстан)
Байтулин И.О. проф., академик (Казахстан)
Банас Иозеф проф. (Польша)
Берсимбаев Р.И. проф., академик (Казахстан)
Велихов Е.П. проф., академик РАН (Россия)
Гашимзаде Ф. проф., академик (Азербайджан)
Гончарук В.В. проф., академик (Украина)
Давлетов А.Е. проф., чл.-корр. (Казахстан)
Джрбашян Р.Т. проф., академик (Армения)
Калимолдаев М.Н. академик (Казахстан), зам. гл. ред.
Лаверов Н.П. проф., академик РАН (Россия)
Лупашку Ф. проф., чл.-корр. (Молдова)
Моход Хасан Селамат проф. (Малайзия)
Мырхалыков Ж.У. проф., академик (Казахстан)
Новак Изабелла проф. (Польша)
Огарь Н.П. проф., чл.-корр. (Казахстан)
Полещук О.Х. проф. (Россия)
Поняев А.И. проф. (Россия)
Сагиян А.С. проф., академик (Армения)
Сатубалдин С.С. проф., академик (Казахстан)
Таткеева Г.Г. проф., чл.-корр. (Казахстан)
Умбетаев И. проф., академик (Казахстан)
Хрипунов Г.С. проф. (Украина)
Юлдашбаев Ю.А. проф., член-корр. РАН (Россия)
Якубова М.М. проф., академик (Таджикистан)

«Вестник Национальной академии наук Республики Казахстан».

ISSN 2518-1467 (Online),

ISSN 1991-3494 (Print)

Собственник: РОО «Национальная академия наук Республики Казахстан» (г. Алматы)

Свидетельство о постановке на учет периодического печатного издания в Комитете информации и архивов Министерства культуры и информации Республики Казахстан №5551-Ж, выданное 01.06.2006 г.

Периодичность: 6 раз в год

Тираж: 2000 экземпляров

Адрес редакции: 050010, г. Алматы, ул. Шевченко, 28, ком. 219, 220, тел. 272-13-19, 272-13-18.

www: nauka-nanrk.kz, bulletin-science.kz

© Национальная академия наук Республики Казахстан, 2018

Адрес типографии: ИП «Аруна», г. Алматы, ул. Муратбаева, 75

E d i t o r i n c h i e f

doctor of chemistry, professor, academician of NAS RK

M. Zh. Zhurinov

E d i t o r i a l b o a r d:

Abiyev R.Sh. prof. (Russia)
Abishev M.Ye. prof., corr. member. (Kazakhstan)
Avramov K.V. prof. (Ukraine)
Appel Jurgen, prof. (Germany)
Baimukanov D.A. prof., corr. member. (Kazakhstan)
Baipakov K.M. prof., academician (Kazakhstan)
Baitullin I.O. prof., academician (Kazakhstan)
Joseph Banas, prof. (Poland)
Bersimbayev R.I. prof., academician (Kazakhstan)
Velikhov Ye.P. prof., academician of RAS (Russia)
Gashimzade F. prof., academician (Azerbaijan)
Goncharuk V.V. prof., academician (Ukraine)
Davletov A.Ye. prof., corr. member. (Kazakhstan)
Dzhrbashian R.T. prof., academician (Armenia)
Kalimoldayev M.N. prof., academician (Kazakhstan), deputy editor in chief
Laverov N.P. prof., academician of RAS (Russia)
Lupashku F. prof., corr. member. (Moldova)
Mohd Hassan Selamat, prof. (Malaysia)
Myrkhalykov Zh.U. prof., academician (Kazakhstan)
Nowak Isabella, prof. (Poland)
Ogar N.P. prof., corr. member. (Kazakhstan)
Poleshchuk O.Kh. prof. (Russia)
Ponyaev A.I. prof. (Russia)
Sagiyani A.S. prof., academician (Armenia)
Satubaldin S.S. prof., academician (Kazakhstan)
Tatkeyeva G.G. prof., corr. member. (Kazakhstan)
Umbetayev I. prof., academician (Kazakhstan)
Khripunov G.S. prof. (Ukraine)
Yuldashbayev Y.A., prof. corresponding member of RAS (Russia)
Yakubova M.M. prof., academician (Tadjikistan)

Bulletin of the National Academy of Sciences of the Republic of Kazakhstan.

ISSN 2518-1467 (Online),

ISSN 1991-3494 (Print)

Owner: RPA "National Academy of Sciences of the Republic of Kazakhstan" (Almaty)

The certificate of registration of a periodic printed publication in the Committee of Information and Archives of the Ministry of Culture and Information of the Republic of Kazakhstan N 5551-Ж, issued 01.06.2006

Periodicity: 6 times a year

Circulation: 2000 copies

Editorial address: 28, Shevchenko str., of. 219, 220, Almaty, 050010, tel. 272-13-19, 272-13-18,
<http://nauka-nanrk.kz/>, <http://bulletin-science.kz>

© National Academy of Sciences of the Republic of Kazakhstan, 2018

Address of printing house: ST "Aruna", 75, Muratbayev str, Almaty

G. T. Sarbaeva¹, A. B. Bayeshov², Yu. P. Zaikov², B. M. Sunnatova¹, K. T. Sarbaeva¹

¹Khoja Akhmet Yassawi International Kazakh-Turkish University, Turkestan, Kazakhstan,

²D. V. Sokolsky Institute of fuel Catalysis and Electrochemistry

²Institute of High-Temperature Electrochemistry, Ural Branch of the Russian Academy of Sciences.

E-mail: gulnar.sarbaeva@mail.ru, bayeshov@mail.ru, dir@ifte.uran.ru,
karlyga.sarbaeva@mail.ru, balym.sunnatova@mail.ru

ELECTROCHEMICAL PROPERTIES OF THALLIUM IN SOLUTIONS CONTAINING NITRATE IONS

Abstract. The electrochemical behavior of the thallium electrode in solutions of sodium nitrate and nitric acid has been studied by the method of removing potentiodynamic polarization curves and by electrolysis. Preliminary studies have shown that thallium electrode does not dissolve in sodium nitrate solution, but it dissolves well in nitric acid. The laws of electrochemical dissolution of a thallium electrode for polarization with an alternating current at a frequency of 50 Hz in solutions of nitric acid was first studied. The influence of a number of electrochemical parameters on the current yield of the product of electrolysis - thallium nitrate (I) is considered. It is shown that the formation of thallium ions (I) with high current efficiency (95-97%). Electrolysis results show that the concentration and temperature of the electrolyte have a significant effect on the current efficiency of Tl (I) ions. It is shown that as the potential of the electrode is increased, the metal is passivated by the formation of thallium hydroxide, an insoluble protective layer, on the electrode surface. As a result of the studies, an effective method for the synthesis of Tl (I) salts has been developed. Carried out an elemental analyzes of the crystals and microphotographic thallium nitrate Tl (I). Due to the fact that thallium salts have low solubility in aqueous solutions, it has been shown that metallic thallium dissolves only in acid solutions under the action of alternating current.

Key words: thallium, micro photography, electrolysis, electrochemistry, electrode, crystal, alternating current, nitric acid, thallium (I) nitrate.

Though thallium and its compounds are poisonous, they are widely used in technics, medicine and other fields. 75% of thallium is used in electronics, electronics and infrared radiation, 7% in agriculture, 3% in medicine, and 15% in other industries.

The chemical and electrochemical properties of thallium have not yet been studied and are significantly different from those characteristic to metals of Group III (Al, In, Ga). Since thallium is dispersed in the environment, its chemical and electrochemical properties are poorly studied. The detection and separation of thallium from the composition of natural minerals and synthesizing its compounds cause difficulties due to its low concentration. The tendency of metal surface to passivity due to oxide shells formation during the electrochemical deposition determines the specificity of electrochemical properties of thallium. As shown by the results of studies dedicated to investigate electrical oxidation and electrical deoxidation processes of thallium, several authors [1-4] show that the kinetics and mechanisms of these processes depend on a number of factors and have significant features.




The authors of work [5-7] have found that passivation of thallium electrode in the anode polarization of HCL or NaCl solutions are carried out in two stages. According to them, thallium ions are formed in the first phase of passivation and in the second phase they become thallium salts. However, the passivation process in the solution of HClO₄ and Na₂SO₄ is carried out in a single phase. In general, the literature review on electrochemical properties of thallium in aqueous solutions indicates that they had been conducted in the field of stationary current and requires replenishment of theoretical data. Moreover, all the known inorganic salts of thallium are obtained by the chemical exchange reaction.

The first study of thallium anode properties began with the release of thallium batteries [6]. Therefore, this work focuses on the oxidation reduction system Tl/Tl_2O_3 . According to the results of the study, the potential of Tl/Tl^+ is that the anode current decreases in the alkaline environment than acids. In [6], it is established that the thallium oxidative ion is in the stationary electrodes with the threshold of tension at the threshold of the polarization hole "b" - 60 mV. It has been pointed out that there is a point of concentration polarization.

In [8], information is given on the electrochemical properties of thallium in the solution of hydrochloric acid and its solubility forming a monovalent compound.

The purpose of this research is to develop effective methods for the synthesis of $Tl(I)$ salts by studying the dependence on various parameters of electrochemical oxidation of thallium electrodes in the presence of alternating current in nitric acid and its salts in solutions of sodium nitrate.

Thallium shows I and III valence in chemical compounds. Its standard electrode potential in aqueous solution has the following value at 25 °C:



Further, studies on the electrochemical dissolution laws of the thallium electrode were continued by shooting cathodic, anode and cyclic potentiodynamic curves in neutral nitrate acid solution and electrolyzing in the neutral nitrate ion solution.

Potentiostat "Autolab" was used for shooting potentiodynamic polarization curves. The experiments were carried out in three electrode cells with separated electrode spaces. As a working electrode, the surface part of thallium wire in 2 mm diameter was used. The second additional electrode was platinum wire. All potential values were compared to silver chlorine electrode immersed in the saturated solution of potassium chloride for "an exclusive clean" analysis (+0,203 V).

When the thallium electrode was immersed in the solution of 100 g/l of sodium nitrate, the potential value "minus" was found to be 0.7 V. The metallic oxidation current is detected on the maximum polarogram when the potential value of thallium is shifted to the anode direction (figure 1). The dissolution rate of thallium does not continue to grow when the potential value "minus" is 0.45 V, from which the metal surface is covered by a thallium nitrate film and remains in the passivation state.




Figure 1 – Anode potentiodynamic polarization curve of the thallium electrode in the sodium nitrate solution:
 $[NaNO_3] = 100\text{g/l}$; $v = 50 \text{ mB/s}$; $t = 25^\circ\text{C}$

Figure 2 shows the cathode polarization curves of the thallium electrode in a solution of sodium nitrate. When the potential of the thallium electrode is shifted to the cathode direction and the minus approximates the potential of 0.6-0.50 V, the oxidation current is detected in the polarogram.




Figure 2 – Cathode potentiodynamic polarization curve of the thallium electrode in the sodium nitrate solution:
 $[\text{NaNO}_3] = 100 \text{ g/l}$; $v = 50 \text{ mV/s}$; $t = 25 \text{ }^\circ\text{C}$

Figure 3 shows the anode-cathode cycle polarization curve of the thallium electrode in the solution of sodium nitrate. When moving the electrode potential towards the positive potential zone, the anode oxidation maximum of the thallium is detected at minus 0.5-0.45 V. It can be argued that the observed maximum occurs due to the oxidation of the thallium (I) nitrate on reaction (1). When the potential of thallium is shifted to the negative values, the maximum oxidation of thallium (I) nitrate formed on its surface is detected and the reduction reaction of the water molecules ions in the potential of "minus" 1,7 V is realized.




Figure 3 – Cathode-anode potentiodynamic polarization curve of the thallium electrode in the sodium nitrate solution:
 $[\text{NaNO}_3] = 100 \text{ g/l}$; $v = 50 \text{ mV/s}$; $t = 25 \text{ }^\circ\text{C}$

Preliminary studies revealed the insolubility of the thallium electrode in a solution of sodium nitrate. The work on the study of electrochemical melting laws of thallium electrode continued with further electrolysis in the nitrogenic acid solution.

Thallium can simultaneously form compounds that are present in two different oxidation states, although its one valence compounds are more stable in the aqueous solution. The ways to obtain inorganic salts of thallium were determined by polarizing its electrochemical properties in the presence of alternating current with frequency of 50 Hz in the HNO₃ solution for the first time and its dissolution through forming one valence compounds was defined.

Preliminary studies revealed the insolubility of the thallium electrode in a solution of sodium nitrate. In the liquefied HNO₃ solution under the alternating current, Tl (I) nitrates are formed in the form of white sediment (figure 4). The formed TlNO₃ salt is poorly soluble in water at room temperature (0.3 g/100g water) and in liquefied acids, and its solubility in hot water increases (100 °C - 1.97 g/100g). The maximum current efficiency of thallium (I) nitrate is 76% for $i=6000\text{A/m}^2$.




Figure 4 – Photos Crystals of Thallium nitrate:
a – formed TlNO₃ crystals; b – 30 times enlarged; c – 100 times enlarged; d – 500 times enlarged

TlNO₃ crystals are formed in HNO₃ solution (1.0-4.0 n) by polarizing thallium electrodes with industrial alternating current of 50 Hz frequency (figure 4,a). The maximum current efficiency of thallium (I) nitrate is 91.6% for $i=8000\text{ A/m}^2$. The influence of HNO₃ concentration on the current efficiency of thallium electrodes in the acidic solutions by forming Tl (I) was investigated. At each phase, thallium electrode (I) is able to dissolve in the anodic half period of the alternating current by forming its ions according to the reaction. At the cathodic half period of the alternating current, hydrogen ions are oxidized on the surface of thallium electrodes:



In conclusion, the results of the research show that, in an optimal condition, the reaction of forming one valence ions basically occurs in the anodic half period on the surface of thallium electrodes, while in the cathodic half period, the reaction of hydrogen gas formation takes place [9].

The effect of the concentration of electrolyte on the current efficiency of thallium (I) ions, which are formed by polarizing thallium (I) electrodes in nitric acid with the help of alternating current is shown in figure 5.




Figure 5 – The electrolyte concentration effect on current formation efficiency of thallium (I) ions:
 $i = 6000 \text{ A/m}^2$, $\tau = 0,5 \text{ h}$; $t = 20 \text{ }^\circ\text{C}$

The initial concentration of nitric acid has a significant effect on the formation of thallium (I) nitrate during the polarization by alternating current. The concentration of the nitric acid solution is obtained within 1.0-4.0 N. Minimal current efficiency of Tl^+ ions is $\sim 76\%$ in 1.0 N. HNO_3 solution. The maximum current efficiency is $\sim 99\%$ in 4.0 N. HNO_3 solutions. The increase of the current efficiency in high concentrations of the nitric acid can be explained by the electrochemical and chemical dissolution processes of the metal. When the concentration of the solution is increased, the recrystallization process takes place as a result of the over-saturation process. The HNO_3 solution prevents the formation of an oxide layer on the surface of the electrode in the anode half-period of alternating current, which ultimately increases the current efficiency of the thallium nitrate formation.

The electrolyte temperature effect on thallium electrodes dissolution processes was investigated between 20-80°C by providing thallium electrodes with the current density of 6000 A/m^2 when polarizing them with alternating current (figure 6). As the electrolyte temperature increases, the current efficiency increases dramatically from 37% to 100%. The loss of electrolyte temperature has a beneficial effect on the electrode processes that occur on the surface of thallium electrodes. This is due to the solubility of Tl (I) nitrate at high temperature.




Figure 6 – Influence of temperature on thallium (I) ion current flow rate:
 $C_{\text{HNO}_3} = 1 \text{ n}$; $\tau = 0.5 \text{ h}$; $i = 6000 \text{ A/m}^2$

The results of the spectral elemental analysis carried on the thallium nitrate composition that has been obtained by the electrochemical way are shown in table.

The result of the analysis on the elemental composition of sediment (TlNO₃) obtained after electrolysis

Spectrum	N	O	Tl	Total
1	8,42	16,45	75,13	100,00
2	8,03	16,03	75,94	100,00
3	8,27	16,30	75,43	100,00
Average	8,24	16,26	75,5	100,00

It is worth noting, the electrochemical property of the thallium in the aqueous solution has not been comprehensively studied yet [10, 11]. Currently, electrochemical study of the properties of rare heavy metals is of great importance [12-21]. The acquisition of new data on the electrochemical properties of the thallium polarized by industrial alternating current highlights the theoretical and practical value of the work. The obtained results contribute to the electrosynthesis field that allows obtaining analytically clean metal compounds.

Electrochemical properties of thallium electrode and its salt were comprehensively investigated in the nitric acid and the sodium nitrate solutions by the method of electrolysis and by shooting potentiodynamic polarization curves.

The results of experiments conducted to investigate the nature of electrode processes in electrochemical oxidation of thallium and the analytical properties of the formed compounds will allow to detect thallium compounds in the field of metal waste and raw materials, as well as to create new ways of obtaining its required compounds.

REFERENCES

- [1] Twidwell L.K., William-Bim S., Williams-Beam C. [Potential technology to remove mine from the mine and process water. Shortened annotation of the literature.] *European Journal of Processing of Mineral Resources and Environmental Protection*. 2002. Vol. 2, N 1. P. 3-10.
- [2] Songina O.A. [Reddy Metal, Metallurgy]. Moscow, 1964. 568 p.
- [3] [Chemistry of Red and Spatial Elements] Sub. red. Bolshackova K.A. M.: Wyssh. school, 1965. 348 p. ISBN 2224-5286
- [4] Chemistry and technology of inferior and diffused elements. Subd. K. A. Bolshakova, Uchebnoye posobie dlya vuzov. Part I. M.: Wyssh. school, 1976. 368 p.
- [5] Pourbaix Marcel. [Atlas of Electrochemical Equilibria in Aqueous Solutions]. Cebelcor; Brussels: Pergaman Press, 1966. 645 p.
- [6] Jonas L. [Electrochemical behavior of thallium] *Z. Electrochem.* 1903. Bd 9. 523 p.
- [7] Muller-Mulhaisen W.J. [Electrochemical behavior of thallium in aqueous solutions] *Z. Electrochem.* 1909. Bd 15. 696 p.
- [8] Sarbayeva G.T., Bayeshov A.B., Matenova M.M., Tuleshova E.Zh. [Ondiristik ainymaly tokpen polarizatsionalangan tallii elektrodynyn tuz khyshkyly eritindisindegi erui]. *Izvestia NAN RK*. 2017. N 2. P. 73-78. ISSN 2224-5286.
- [9] Matenova M., Sarbayeva G. Ainymaly tokpen polarizatsionalangan tallii elektrodynyn tuz khyshkyly eritindisindegi electroximialyk khasieti. *Khalykharalyk gylymi-tajiribelik konferensia materialdary [Bilim, gylym zhane ondiristi integratsionalau koncepciasy-2]*. Shymkent, 2016. P. 251-253. (In Kaz.)
- [10] Sinyakova M.A., Semenova E.A., Gamuletskaya O.A. Published in *Ekologicheskaya Khimiya*. 2013. Vol. 22, N 4. P. 234-238. DOI:10.1134/S1070363214130040 (In Eng.)
- [11] Usipbekova E.Zh. [Electrochemical conveying of talliol in different electrolytes] *Vestnik KazNU Series chem.* 2014. Vol. 74, N 2. P. 47-52. (In Kaz.)
- [12] Usipbekova E.Zh. [Electrochemical refining of the thallium in the neutral medium] *Proceedings of NAN RK. Series of chemistry and technology*. 2014. Vol. 408, N 5. P. 64-69.
- [13] Seylhanova G.A. [Voltammetry of thallium in various electrolyteselectroacross] Conference, FCT-UNL, September 11-12. Portugal, 2014. International conference on international conferences. 2014. Vol. 1, N 1. P. 51-52.
- [14] Ivanov A.V., Bredyuk O.A., Gerasimenko A.V., Lutsenko I.A., Antzutkin O.N., Forsling W. Published in *Koordinatsionnaya Khimiya*. 2006. Vol. 32, N 5. P. 354-364. DOI:10.1134/S107032840605006X (In Eng.)
- [15] Baeshov A., Abiyjanova D. Dzhurinov M.Zh. [Electrochemical adhesion in India to dissolve sodium chloride in polarization with non-stationary current]. Report NAN RK. 2009. N 1. P. 13-16.
- [16] Babanly L.F. Mashadieva M.B. Babanly, 2017, Published in *Neorganicheskie Materialy*. 2017. Vol. 53, N 5. P. 524-529. DOI:10.1134/S002016851705003X (In Eng.)
- [17] Seylhanova G.A., Kurbatov A.P., Berezovsky A.V., Usipbekova E.Zh., Nauryzbaev M.K. Electrochemical deposition and dissolution of oxide tall (III). *Izvestia NAN RK*. 2016. N 5. P. 200-205. ISSN 2224-5286.
- [18] Lidin R.A. et al. [Chemical properties of neuronc phenomena], *Ucheb.posobyie dlya vuzov*. 3-e izd., ispr. M.: Chemistry, 2000. 480 p. ISBN 5-7245-1163-0.
- [19] Levitsky C.A., Aldamzharova S.H., Zebreva A.I. [Electrochemical conveying of the tallow on the porous and gallium electrodes]. *Izvestia AN KazSSR. The series is chemically*. 1983. N 36. P. 26-287.

[20] V.A. Popkov, S.A. Puzakov. General Chemistry. M.: Publishing house [GOETTAR-MEDIA], 2014, 374-382.

[21] Kunkely H., Vogler A. Monatshefte für Chemie (2004) 135. DOI: 10.1007/s00706-003-0103-4. Online ISSN:1434-4475.

Г. Т. Сарбаева¹, А. Б. Башов², Ю. П. Зайков², Б. М. Сүннатов¹, Қ. Т. Сарбаева¹

¹Қожа Ахмет Ясауи атындағы Халықаралық қазақ-түрік университеті, Түркістан, Қазақстан,

²«Д. В. Сокольский атындағы Жанармай, катализ және электрохимия институты» АҚ, Алматы, Қазақстан,

²«РФАУаЖТЭИ», Екатеринбург, Россия

ТАЛЛИЙДІҢ НИТРАТ ИОНДАРЫ БАР ЕРІТІНДІЛЕРДЕГІ ЭЛЕКТРОХИМИЯЛЫҚ ҚАСИЕТІ

Аннотация. Таллий электродының натрий нитраты және азот қышқылы ерітінділеріндегі электрохимиялық қасиеті потенциодинамикалық поляризациялық қисықтар түсіру арқылы және электролиз жүргізу арқылы зерттелді. Алдын ала жүргізілген зерттеулер таллий электродының натрий нитраты ерітіндісінде ерімейтіндігін, ал азот қышқылы ерітіндісінде жақсы еритіндігін көрсетті. Алғаш рет таллий электродының азот қышқылы ерітіндісіндегі электрохимиялық еру заңдылықтары жиілігі 50 Гц өндірістік айнымалы ток қатысында зерттелді. Электролиз өнімі - таллий (I) нитратының түзілуінің ток бойынша шығымына бірқатар электрохимиялық параметрлердің әсері қарастырылды. Азот қышқылы ерітіндісінде таллий (I) иондарының жоғары ток бойынша шығыммен (95-97%) түзілетіндігі көрсетілді. Электролиз нәтижелері TI (I) иондарының түзілуінің ток бойынша шығымына - электролит концентрациясы мен температурасының елеулі әсері бар екендігін көрсетті. Электрод потенциалының өсуі, электрод бетінде ерімейтін қорғаныштық қабат - таллий қосылысының түзілуіне байланысты металды пассивті күйге түсіретіндігі көрсетілді. Жүргізілген зерттеулердің нәтижесінде TI (I) тұздарын синтездеудің тиімді әдісі жасалды. Түзілген таллий (I) нитраты кристалдарының құрамына элементтік анализ және микрофотографиялық сараптамалар жасалды. Таллий (I) тұздарының судағы ерігіштігі төмен болғандықтан, таллий тек қышқылды ерітінділерде айнымалы ток әсерімен еритіндігі көрсетілді.

Түйін сөздер: таллий, микрофотография, электролиз, электрохимия, электрод, кристалл, айнымалы ток, азот қышқылы, таллий (I) нитраты.

Г. Т. Сарбаева¹, А. Б. Башов², Ю. П. Зайков², Б. М. Сүннатов¹, Қ. Т. Сарбаева¹

¹Международный казахско-турецкий университет им. Ходжи Ахмеда Ясави, Туркестан, Казахстан,

²АО «Институт топлива, катализа и электрохимии им. Д. В. Сокольского», Алматы, Казахстан,

²«ИВТЭУрОРАН», Екатеринбург, Россия

ЭЛЕКТРОХИМИЧЕСКОЕ ПОВЕДЕНИЕ ТАЛЛИЯ В РАСТВОРАХ, СОДЕРЖАЩИХ НИТРАТ-ИОНЫ

Аннотация. Методом снятия потенциодинамических поляризационных кривых и методом электролиза изучено электрохимическое поведение таллиевого электрода в растворах нитрата натрия и азотной кислоты. Предварительные исследования показали, что таллиевый электрд не растворяется в растворе нитрата натрия, но хорошо растворяется в азотной килоте. Впервые исследованы закономерности электрохимического растворения таллиевого электрода при поляризации переменным током с частотой 50 Гц в азотнокислых растворах. Рассмотрено влияние ряда электрохимических параметров на выход по току продукта электролиза - нитрата таллия (I). Показано, что происходит образование ионов таллия (I) с высокими выходами по току (95-97%). Результаты электролиза показывают, что концентрация и температура электролита оказывают значительное влияние на выход по току образования ионов TI (I). Показано, что при увеличении потенциала электрода металл пассивируется вследствие образования на поверхности электрода нерастворимого защитного слоя - соединения таллия. В результате проведенных исследований разработан эффективный способ синтеза солей TI (I). Проведены элементный и микрофотографический анализы кристаллов нитрата таллия TI (I). В связи с тем, что соли таллия имеют низкую растворимость в водных растворах, было показано, что металлический таллий растворяется только в растворах кислот под действием переменного тока.

Ключевые слова: таллий, микрофотография, электролиз, электрохимия, кристалл, переменный ток, азотная кислота, нитрат (I) таллия.

Publication Ethics and Publication Malpractice in the journals of the National Academy of Sciences of the Republic of Kazakhstan

For information on Ethics in publishing and Ethical guidelines for journal publication see <http://www.elsevier.com/publishingethics> and <http://www.elsevier.com/journal-authors/ethics>.

Submission of an article to the National Academy of Sciences of the Republic of Kazakhstan implies that the described work has not been published previously (except in the form of an abstract or as part of a published lecture or academic thesis or as an electronic preprint, see <http://www.elsevier.com/postingpolicy>), that it is not under consideration for publication elsewhere, that its publication is approved by all authors and tacitly or explicitly by the responsible authorities where the work was carried out, and that, if accepted, it will not be published elsewhere in the same form, in English or in any other language, including electronically without the written consent of the copyright-holder. In particular, translations into English of papers already published in another language are not accepted.

No other forms of scientific misconduct are allowed, such as plagiarism, falsification, fraudulent data, incorrect interpretation of other works, incorrect citations, etc. The National Academy of Sciences of the Republic of Kazakhstan follows the Code of Conduct of the Committee on Publication Ethics (COPE), and follows the COPE Flowcharts for Resolving Cases of Suspected Misconduct (http://publicationethics.org/files/u2/New_Code.pdf). To verify originality, your article may be checked by the Cross Check originality detection service <http://www.elsevier.com/editors/plagdetect>.

The authors are obliged to participate in peer review process and be ready to provide corrections, clarifications, retractions and apologies when needed. All authors of a paper should have significantly contributed to the research.

The reviewers should provide objective judgments and should point out relevant published works which are not yet cited. Reviewed articles should be treated confidentially. The reviewers will be chosen in such a way that there is no conflict of interests with respect to the research, the authors and/or the research funders.

The editors have complete responsibility and authority to reject or accept a paper, and they will only accept a paper when reasonably certain. They will preserve anonymity of reviewers and promote publication of corrections, clarifications, retractions and apologies when needed. The acceptance of a paper automatically implies the copyright transfer to the National Academy of Sciences of the Republic of Kazakhstan.

The Editorial Board of the National Academy of Sciences of the Republic of Kazakhstan will monitor and safeguard publishing ethics.

Правила оформления статьи для публикации в журнале смотреть на сайте:

www.nauka-nanrk.kz

ISSN 2518-1467 (Online), ISSN 1991-3494 (Print)

<http://www.bulletin-science.kz/index.php/ru/>

Редакторы *М. С. Ахметова, Т. М. Апендиев, Д. С. Аленов*
Верстка на компьютере *Д. Н. Калкабековой*

Подписано в печать 06.03.2018.
Формат 60x881/8. Бумага офсетная. Печать – ризограф.
14,2 п.л. Тираж 500. Заказ 2.